



AUSTENITIC STAINLESS STEEL Roldamax® - ACX 076	
EN DESIGNATION	AISI DESIGNATION
1.4305	303
X8CrNiS18-9	



DESCRIPTION ACX 076 is Roldan's own development of AISI 303. It is part of the ROLDAMAX series, which is composed by those steel grades with improved machinability. In addition to its excellent machinability, it has a good corrosion and mechanical strength. The addition of Sulphur improves the chip removal in the processes of cutting and forming, turning, drilling, slotting, or parting, improving the performance of these processes and increasing the lifespan of tools.

CHEMICAL COMPOSITION

C	Si	Mn	P	S	N(ppm)	Cr	Cu	Mo	Ni	Ti
≤0.10	≤0.75	1.50-2.00	≤0.045	0.25-0.35	≤1000	17.00-19.00	-	-	8.00-9.00	-

APPLICATIONS

Roldamax® ACX 076 steel grade, Roldan's high machinability steel grade, is used in all those elements that need specific properties for their machinability:

- Shafts
- Nuts
- Bolts
- Gears
- Hubs
- Accessories for the automotive and aerospace industries

MECHANICAL PROPERTIES
EN 10088-3

	Rp _{0.2} (MPa)	Rm (MPa)	Elongation (%)	Hardness (HB)
Wire Rod	≥190	500-750	≥35	≤230
Bar	190-400	500-950	15-35	-

PHYSICAL PROPERTIES

Elastic modulus	Thermal expansion average coefficient (20°C-100°C)	Thermal conductivity	Electrical resistivity	Density
190 Gpa	16 µm/m°C	15 W/m·k	0.73 Ω·mm²/m	7.9 kg/dm³

WELDING

The consumables recommended are the following:

Covered electrodes	Wires and rods	Hollow electrodes
E 19 9 L	G 19 9 L (GMAW)	T 19 9 L
308L	W 19 9 L (GTAW)	308L
	P 19 9 L (PAW)	
	S 19 9 L (SAW)	
	308L	

MACHINABILITY

In the Roldamax® series, the addition of Sulphur is used to improve the machinability of austenitic stainless steels. In ACX 076 this improvement is noticed in a higher lifespan of the tools, less roughness in the final finish and higher productivity.

Moreover, ACX 076 presents great homogeneity in its performance regarding the heat. Treatments like the addition of Ca, among others, improve the performance and outputs of ACX 076.

CORROSION RESISTANCE

This steel grade's corrosion resistance with the addition of Sulphur has been optimized to reach a balance with its machinability.

Its atmospheric corrosion resistance is good although in marine atmospheres or with high pollution, stain issues can appear.

It has a good corrosion resistance under stress conditions.



Roldamax® - ACX 076 | AUSTENITIC STAINLESS STEEL



SPECIFICATIONS | It can be supplied in accordance with the requirements of standards 10088-3 and ASTM 581.

CERTIFICACIONES

	Sistema de Gestión	
	ISO 9001:2015 ISO 14001:2015 ISO 50001:2018	
www.tuv.com ID 0091003143		



Disclaimer

The material contained in this manual has been designed as a guide for customers at Acerinox, S.A.. However, the material contained herein is not intended as a substitute for any person's procedures and should not be used or relied upon for any specific or general application without first obtaining competent advice. Furthermore, Acerinox, S.A. disclaims any responsibility for the suitability of the stainless steel in question for any particular purpose or for the performance or selection of the stainless steel, unless Acerinox, S.A. specifically and expressly authorises the purpose or selection. The material contained in this manual does not purport to be a comprehensive or exhaustive statement of all relevant material applicable to special and general stainless steel products and no representation, condition or warranty, express or implied, is given by Acerinox, S.A. as to the accuracy or completeness of this manual and, so far as is permitted by law, Acerinox, S.A., its members, staff and consultants disclaim any duty of care in relation to the preparation of this manual and the information that it contains and shall not be liable for any direct, indirect or consequential loss, damage or injury suffered by any person, howsoever caused as a result of relying on any statement in or omission to this manual and any such liability is expressly disclaimed. [Acerinox, S.A. shall not be liable in the event of a breakdown, malfunction or failure occurring due to faulty design, material or workmanship of the stainless steel, whether based on the information contained herein or not, and shall not, under any circumstances, be liable for any damages, either director indirect, particularly consequential damages, including but not limited to damages far loss of profits.]