



AUSTENITIC STAINLESS STEEL ACX 217	
DESIGNACIÓN EN	AISI DESIGNACIÓN
1.4307	304L
X2CrNi18-9	



DESCRIPTION ACX 217 belongs to the range of austenitic Cr-Ni steels. These steels are the most versatile steels on the market making them suitable for a multitude of applications. These steels combine good corrosion resistance in a wide range of environments with outstanding mechanical properties. ACX 217, due to its low carbon content, is less susceptible to intergranular corrosion in welds than ACX 126.

CHEMICAL COMPOSITION

C	Si	Mn	P	S	N(ppm)	Cr	Cu	Mo	Ni	Ti
≤0.03	≤0.75	≤2.00	≤0.045	≤0.030	≤1000	18.00-20.00	-	-	8.50-9.50	-

APPLICATIONS

- Pipes
- Boiler making
- Chemical industry
- Cryogenic applications

MECHANICAL PROPERTIES
EN10088-3

	Rp _{0,2} (MPa)	Rm (MPa)	Elongation (%)	Hardness (HB)
Wire rod	≥175	500-700	≥45	≤215
Bar	≥175	500-930	≥25	-

PHYSICAL PROPERTIES

Elastic modulus	Thermal expansion average coefficient (20°C-100°C)	Thermal conductivity	Electrical resistivity	Density
200 Gpa	16 μm/m°C	15 W/m·k	0.73 Ω·mm ² /m	7.9 kg/dm ³

WELDING

The consumables recommended are the following:

Covered electrodes	Wires and rods	Hollow electrodes
E 19 9 Nb	G 19 9 L (GMAW) W 19 9 L (GTAW) P 19 9 L (PAW) S 19 9 L (SAW)	T 19 9 L
308L	308L	308L

INTERGRANULAR CORROSION

ACX 217, due to its low C content (≤ 0.03%), is less susceptible to intergranular corrosion than ACX 126.

CORROSION RESISTANCE

The austenitic stainless steels of the Cr-Ni family provide good corrosion resistance performance in a large number of applications. As an example, these steels present corrosion rates of less than 0.10 mm/year in the following environments:

- 20% acetic acid at 80°C.
- 90% formic acid at 20°C.
- 20% phosphoric acid at 60°C.
- Nitric acid 20% at 50°C.
- Sulphuric acid 90% at 20°C.



ACX 217 | AUSTENITIC STAINLESS STEEL



SPECIFICATIONS | Can be supplied in accordance with the requirements of standards 10088-3 and ASTM/ASME A/SA-276 condition A.

CERTIFICATES



Sistema de Gestión
 ISO 9001:2015
 ISO 14001:2015
 ISO 50001:2018



www.tuv.com
 ID 0091003143



Disclaimer

The material contained in this manual has been designed as a guide for customers at Acerinox, S.A.. However, the material contained herein is not intended as a substitute for any person's procedures and should not be used or relied upon for any specific or general application without first obtaining competent advice. Furthermore, Acerinox, S.A. disclaims any responsibility for the suitability of the stainless steel in question for any particular purpose or for the performance or selection of the stainless steel, unless Acerinox, S.A. specifically and expressly authorises the purpose or selection. The material contained in this manual does not purport to be a comprehensive or exhaustive statement of all relevant material applicable to special and general stainless steel products and no representation, condition or warranty, express or implied, is given by Acerinox, S.A. as to the accuracy or completeness of this manual and, so far as is permitted by law, Acerinox, S.A., its members, staff and consultants disclaim any duty of care in relation to the preparation of this manual and the information that it contains and shall not be liable for any direct, indirect or consequential loss, damage or injury suffered by any person, howsoever caused as a result of relying on any statement in or omission to this manual and any such liability is expressly disclaimed. [Acerinox, S.A. shall not be liable in the event of a breakdown, malfunction or failure occurring due to faulty design, material or workmanship of the stainless steel, whether based on the information contained herein or not, and shall not, under any circumstances, be liable for any damages, either director indirect, particularly consequential damages, including but not limited to damages for loss of profits.]