



AUSTENITIC STAINLESS STEEL Roldamax® - ACX 229	
EN DESIGNATION	AISI EN DESIGNATION
1.4307	304L
X2CrNi18-9	



DESCRIPTION ACX 229 is part of the Roldamax® steel grade series. This specific steel grade was developed based on steel grade AISI 304L. Roldan applied its long products production expertise in order to reach all of 304L's properties, as well as the improved machinability that the entire Roldamax® steel grade series offers.

CHEMICAL COMPOSITION	C	Si	Mn	P	S	N(ppm)	Cr	Cu	Mo	Ni	Ti
	≤0.03	≤0.75	≤2.00	≤0.045	0.020-0.030	≤1000	18.00-18.30	-	-	8.00-8.50	-

APPLICATIONS ACX 229, one of Roldan's Roldamax® high machinability steel grades, is used in any element that requires specific properties for its machinability:

- Shafts
- Nuts
- Bolts
- Gears
- Hubs
- Accessories for the automotive and the aerospace industries.

MECHANICAL PROPERTIES EN 10088-3	Rp _{0.2} (MPa)	Rm (MPa)	Elongation (%)	Hardness (HB)
Wire rod	≥175	500-700	≥45	≤215
Bar	≥175	500-930	≥25	-

PHYSICAL PROPERTIES	Elastic modulus	Thermal expansion average coefficient (20°C-100°C)	Thermal conductivity	Electrical restivity	Density
	200 Gpa	16 µm/m°C	15 W/m·k	0.47 Ω·mm ² /m	7.9 kg/dm ³

WELDING The consumables recommended are the following:

Covered electrodes	Wires and rods	Hollow electrodes
E 19 9 L	G 19 9 L (GMAW)	T 19 9 L
308L	W 19 9 L (GTAW)	308L
	P 19 9 L (PAW)	
	S 19 9 L (SAW)	
	308L	

MACHINABILITY The addition of sulphur is employed to improve the machinability of Roldamax® steel grades, achieving a longer tool lifespan, higher machining speed and a better chip.

INTERGRANULAR CORROSION Due to its low C content (≤ 0,03%), ACX 229 is less sensitive than ACX 109 to suffer intergranular corrosion.

CORROSION RESISTANCE Austenitic stainless steels of family Cr-Ni present good corrosion resistance features in numerous applications. In example, these steel grades present corrosion speeds lower than 0,10mm/year in the following environments:

- Acetic acid 20% at 80°C.
- Formic acid 90% at 20°C.
- Phosphoric acid 20% at 60°C.
- Nitric acid 20% at 50°C.
- Sulphuric acid 90% at 20°C



Roldamax® - ACX 229 | AUSTENITIC STAINLESS STEEL



SPECIFICATIONS | It can be supplied in accordance with requirements of standards 10088-3 & ASTM A-479 "Condition: A"

CERTIFICATES



Sistema de Gestión
ISO 9001:2015
ISO 14001:2015
ISO 50001:2018



www.tuv.com
ID 0091003143



Disclaimer

The material contained in this manual has been designed as a guide for customers at Acerinox, S.A.. However, the material contained herein is not intended as a substitute for any person's procedures and should not be used or relied upon for any specific or general application without first obtaining competent advice. Furthermore, Acerinox, S.A. disclaims any responsibility for the suitability of the stainless steel in question for any particular purpose or for the performance or selection of the stainless steel, unless Acerinox, S.A. specifically and expressly authorises the purpose or selection. The material contained in this manual does not purport to be a comprehensive or exhaustive statement of all relevant material applicable to special and general stainless steel products and no representation, condition or warranty, express or implied, is given by Acerinox, S.A. as to the accuracy or completeness of this manual and, so far as is permitted by law, Acerinox, S.A., its members, staff and consultants disclaim any duty of care in relation to the preparation of this manual and the information that it contains and shall not be liable for any direct, indirect or consequential loss, damage or injury suffered by any person, howsoever caused as a result of relying on any statement in or omission to this manual and any such liability is expressly disclaimed. [Acerinox, S.A. shall not be liable in the event of a breakdown, malfunction or failure occurring due to faulty design, material or workmanship of the stainless steel, whether based on the information contained herein or not, and shall not, under any circumstances, be liable for any damages, either director indirect, particularly consequential damages, including but not limited to damages for loss of profits.]