

7% NICKEL AUSTENITIC STAINLESS STEEL ACX 110				
EN DESIGNATION	ASTM DESIGNATION			
1.4310	301			
X10CrNi18-8	S30100			

DESCRIPTION | ACX 110 austenitic stainless steel exhibits high toughness, corrosive atmosphere resistance and surface brightness. All of this makes it an excellent choice for structural and decorative applications. Moreover, ACX 110 offers good weldability properties and can be obtained as annealed product or with different hardness grades.

CHEMICAL COMPOSITION

С	Si	Mn	Р	S	Cr	Ni	Mo	N
≤0.15	≤1.00	≤2.00	≤0.045	≤0.015	17.00-18.00	6.00-8.00	≤0.80	≤0.10

APPLICATIONS - Architectural and automotive decorative elements

- Food industry
- Tableware, household
- Aeronautical components
- Railway cars and trucks superstructures
- Springs

MECHANICAL PROPERTIES AFTER COLD ROLLING AND FINAL ANNEALING

Rp _{0.2}	> 250 N/mm ²		
Rp _{1.0}	> 280 N/mm ²		
Rm	600 - 950 N/mm ²		
Elongation	min 40%		
Hardness	max 200 HB		

PROPERTIES

PHYSICAL At 20°C has a density of 7.9 kg/dm³ and a specific heat of 500 J/kg·K

	20°C	100ºC	200ºC	300°C	400ºC	500°C
Modulus of elasticity (GPa)	200	194	186	179	172	165
Mean coefficient of linear expansion between 20°C (10° x K·1) and	-	16	17	17	18	18
Thermal conductivity (W/m·K)	15	16.2	-	-	-	21.4
Electrical resistivity (Ω·mm²/m)	0.73	-	-	-	-	-

WELDING | Recommended consumable electrodes:

Shielded electrodes	Wires and rods	Hollow electrodes
E 19 9 308	G 19 9 L (GMAW) W 19 9 L (GTAW) P 19 9 L (PAW) S 19 9 L (SAW) 308 308L	T 19 9 L 308

RESISTANCE

CORROSION | The corrosion resistance of ACX 100 is slightly lower than ACX 120. It is more likely to suffer intergranular corrosion.

In case of carbide precipitation during welding processes ACX 150 is recommended. It is suitable for urban environments and food handling applications.



ACX 110 | 7% NICKEL AUSTENITIC STAINLESS STEEL

TEMPERATURE OXIDATION RESISTANCE

This stainless steel is not recommended at temperatures above 870° C. The oxidation rate is highly affected by the atmosphere to which the material is exposed, warming and cooling cycles and structural design, therefore no general data is provided.

SURFACE **CLEANING**

Wash the surface with neutral soap and water applied with a cloth or a brush without scratching the stainless steel. Then, always rinse the stainless steel with water to remove completely the cleaning agent. Finally, it is recommended to dry the surface to preserve a good superficial condition. In severe environments, a frequent cleaning is strongly recommended.

SPECIFICATIONS | It can be delivered according to EN, ASTM, ASME standards requirements.

It complies with the European Directives:

- Food industry, RE 1935/2004.
- Hexavalent chromium, ROHS.
- Electrical instruments, ROHS.