



REFRACTORY AUSTENITIC STAINLESS STEEL ACX 350	
EN DESIGNATION	ASTM DESIGNATION
1.4845	310S
X8CrNi25-21	S31008

DESCRIPTION Refractory austenitic stainless steel ACX 350 has high mechanical resistance, toughness and excellent high-temperature oxidation resistance, as a result of its high chromium and nickel content. The low carbon level reduces carbide precipitation during welding or high temperature applications. It is more resistant to high-temperature oxidation than ACX 340.

CHEMICAL COMPOSITION	C	Si	Mn	P	S	Cr	Ni
	≤0.08	≤0.75	≤2.00	≤0.035	≤0.015	24.00-26.00	19.00-21.00

APPLICATIONS

- Electric resistances
- Furnaces
- High-temperature applications
- Air heaters

MECHANICAL PROPERTIES AFTER COLD ROLLING AND FINAL ANNEALING	Property	Value
	Rp_{0.2}	>240 N/mm ²
	Rm	540 - 700 N/mm ²
	Elongation	> 40%
	Hardness	< 200 HB

PHYSICAL PROPERTIES At 20°C it has a density of 7.9 kg/dm³ and a specific heat of 500 J/kg·K

	20°C	200°C	400°C	600°C	800°C	1000°C
Modulus of elasticity (GPa)	200	186	173	157	130	-
Mean coefficient of linear expansion between 20°C (10⁻⁶ x K⁻¹) and	-	15,5	17	17.5	18.5	19
Thermal conductivity (W/m·K)	15	16	18	21	24	27
Electrical resistivity (Ω·mm²/m)	0.85	0.90	1.06	1.19	1.25	1.38

WELDING The recommended consumable electrodes are:

Shielded electrodes	Wires and rods	Hollow electrodes
E 25 20	G 25 20 (GMAW) W 25 20 (GTAW)	T 25 20
ER 310	P 25 20 (PAW) S 25 20 (SAW)	ER 310
ER Ni Cr 3	ER 310 ER Ni Cr 3	ER Ni Cr 3

CORROSION RESISTANCE These steels are optimized at high temperature. When used in other media, these steels are equivalent to any other general-purpose austenitic stainless steel.

PITTING CORROSION As any Cr-Ni steel, ACX 350 can be successfully used in chloride media with a concentration not higher than 100 ppm.



HIGH-TEMPERATURE OXIDATION RESISTANCE

As a result of their high chromium and nickel contents, these steels have high corrosion resistance at high temperature.

Maximum operating temperatures for ACX 350 in continuous working in different media are:

- (a) Oxidizing media 1100°C
- (b) Oxidizing media with sulphur 1000°C
- Carburizing reducing media 1000°C
- Sulphidizing reducing media 750°C

When the environment is not continuously oxidizing, the thermal death points are smaller than the ones above (a, b) and they depend on the cycling frequency. In any case they should not exceed 950°C.

It is recommended in case of thermal crash risk and it is better in carburizing media than ACX 340. It can also be used in fused salt baths.

SURFACE CLEANING

Wash the surface with neutral soap and water applied with a cloth or a brush without scratching the stainless steel. Then, always rinse the stainless steel with water to remove completely the cleaning agent. Finally, it is recommended to dry the surface to preserve a good superficial condition. In severe environments, a frequent cleaning is strongly recommended.

SPECIFICATIONS

ACX 350 austenitic stainless steel is included in the main international standards.

This grade can be supplied according to EN, ASTM and ASME standard requirements.

ACX 350 complies with the European Directives:

- Food industry, RE 1935/2004.
- Hexavalent chromium, ROHS.
- Electrical instruments, ROHS.

Disclaimer

The material contained in this manual has been designed as a guide for customers at Acerinox, S.A.. However, the material contained herein is not intended as a substitute for any person's procedures and should not be used or relied upon for any specific or general application without first obtaining competent advice. Furthermore, Acerinox, S.A. disclaims any responsibility for the suitability of the stainless steel in question for any particular purpose or for the performance or selection of the stainless steel, unless Acerinox, S.A. specifically and expressly authorises the purpose or selection. The material contained in this manual does not purport to be a comprehensive or exhaustive statement of all relevant material applicable to special and general stainless steel products and no representation, condition or warranty, express or implied, is given by Acerinox, S.A. as to the accuracy or completeness of this manual and, so far as is permitted by law, Acerinox, S.A., its members, staff and consultants disclaim any duty of care in relation to the preparation of this manual and the information that it contains and shall not be liable for any direct, indirect or consequential loss, damage or injury suffered by any person, howsoever caused as a result of relying on any statement in or omission to this manual and any such liability is expressly disclaimed. [Acerinox, S.A. shall not be liable in the event of a breakdown, malfunction or failure occurring due to faulty design, material or workmanship of the stainless steel, whether based on the information contained herein or not, and shall not, under any circumstances, be liable for any damages, either direct or indirect, particularly consequential damages, including but not limited to damages for loss of profits.]